

Indetex nv
Rue du Mont Gallois 58
7700 MOUSCRON

Your notice of
27-03-2025

Your reference

Date
08-04-2025

Analysis Report 25.01714.01


Required tests :

EN 13773 (2003)

Sample id	Information given by the client	Date of receipt
T2506900	CORVO	27-03-2025

Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Samples

T2506900
CORVO





Reference: T2506900 - CORVO

Washing and drying

Date of ending the test	03-04-2025
Standard used	ISO 6330 (2000) + A1 (2008), ISO 6330 (2012)
Deviation from the standard	-
Conditioning	20°C, relative humidity 65%
Apparatus	Wascator FOM 71 (type A)
Used detergent	ECE detergent (Type 3)
Washing method and temperature	8A- 30°C (2000)
Drying method	A = Line dry (2000)
Number of washing cycles	3
Mass of the test specimens	1355 g
Mass of the ballast	The washing machine is filled with ballast to achieve 2 kg in total
Remark	Washing always occurs with a ballast type III 100% PES regardless of the composition of the fabric.

Sample generated: T2506900_02d

Reference: T2506900_02d - CORVO

Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.

Date of ending the test 07-04-2025
Standard used EN 1101 (1995) + A1 (2005)
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%
Testing atmosphere 22°C, relative humidity 27%

Dimension of the specimens 200 mm x 80 mm

Ignition Bottom edge

The test specimens have been washed 3 times instead of 1 time.*

*Based on information given by the client.

Length

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated
No ignition within 20 s



Width

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated
No ignition within 20 s

Minimum ignition time

No ignition within 20 s

Reference: T2506900_02d - CORVO

Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.

Date of ending the test 08-04-2025
Standard used EN 13772 (2011)
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have been washed 3 times instead of 12 times.*

*Based on information given by the client.

Length

	Face A	Face B	Face B	Face B
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	150	160	150	155
Flaming debris	no	no	no	no

Width

	Face A	Face B	Face B	Face B
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	145	155	155	160
Flaming debris	no	no	no	no



Reference: T2506900 - CORVO

Classification of curtains and drapes according to EN 13773

Product standard EN 13773 (2003)

Provisional classification* in accordance with EN 13773: Class 1

Classification based on*:
EN 1101 after 3 washes.
EN 13772 after 3 washes.

A final classification can only be assigned after having carried out:
EN 1101 after 1 wash.
EN 13772 on original material.
EN 13772 after 12 washes.