

Our Ref: SW/LS/BR

30 April 2019

Report 340800

Page 1 of 3

Indetex NV
Rue du Mont Gallois 58
7700 Mouscron
Belgium

Contact: Mike Debonnet

DATE RECEIVED	:	01 APRIL 2019
QUALITY REFERENCE	:	SALERNO
REPUTED FIBRE CONTENT	:	NOT GIVEN
FABRIC DESCRIPTION	:	WOVEN
COLOUR/DESIGN	:	GREY

REQUEST: Flammability in accordance with IMO resolution A471 (X11) as amended by Resolution A563

COMMENT: See results below



S. WISEMAN
LABORATORY DIRECTOR

L. SHERIDAN
LABORATORY MANAGER

This report shall not be reproduced except in full without written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.

*This test has been sub-contracted

Our Ref: SW/LS/BR

30 April 2019

Report 340800

Page 2 of 3

Flammability in accordance with IMO 471 (x11) Resolution A563 Part 7

Conditioning

A minimum of 24 hours at 65±5% Relative Humidity, 20±5°C

Report

Flame application time: 15 seconds

Mode of flame application: Face ignition

The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a configuration.

Face	Warp direction					Weft direction				
Specimen number	1	2	3	4	5	1	2	3	4	5
Flame reached and edge (✓ or X)	X	X	X	X	X	X	X	X	X	X
Hole reach an edge (✓ or X)	X	X	X	X	X	X	X	X	X	X
Surface flash (✓ or X)	X	X	X	X	X	X	X	X	X	X
Duration of flaming (s)	0	0	0	0	2	0	0	0	0	0
Length of char (mm)	79	95	84	107	92	103	148	85	95	56
Ignition of Cotton wool (Y/N)	N	N	N	N	N	N	N	N	N	N

Mean Char Length Warp= 91.4mm Weft= 97.4mm

Back	Warp direction					Weft direction				
Specimen number	1	2	3	4	5	1	2	3	4	5
Flame reached and edge (✓ or X)	X	X	X	X	X	X	X	X	X	X
Hole reach an edge (✓ or X)	X	X	X	X	X	X	X	X	X	X
Surface flash (✓ or X)	X	X	X	X	X	X	X	X	X	X
Duration of flaming (s)	0	0	0	0	0	0	0	0	0	0
Length of char (mm)	82	80	83	84	68	70	82	76	88	83
Ignition of Cotton wool (Y/N)	N	N	N	N	N	N	N	N	N	N

Mean Char Length Warp= 79.4mm Weft= 79.5mm

Our Ref: SW/LS/BR

30 April 2019

Report 340800

Page 3 of 3

Comments

On the basis of the tests carried out this sample of fabric meets the performance criteria for curtains and drapes as specified in Clause 3 of IMO 471 (X11) Resolution A563 Part 7