

Our Ref: SW/LS/BR

07 March 2019

**Report 337184**

**Page 1 of 3**

Indetex Nv  
Rue du Mont Gallois 58  
7700 Mouscron  
Belgium

Contact: Mike Debonnet

---

DATE RECEIVED	:	01 FEBRUARY 2019
QUALITY REFERENCE	:	SOFTLINE
REPUTED FIBRE CONTENT	:	100% POLYESTER ACRYLIC-COATED
FABRIC DESCRIPTION	:	COATED
COLOUR/DESIGN	:	COLORED FLOCK RANGE
END USE	:	BLACKOUT CURTAIN

---

REQUEST: Flammability in accordance with IMO resolution A471 (X11) as amended by Resolution A563

---

COMMENT: See results below

---



**S. WISEMAN**  
**LABORATORY DIRECTOR**

**L. SHERIDAN**  
**LABORATORY MANAGER**

This report shall not be reproduced except in full without written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.

\*This test has been sub-contracted

Our Ref: SW/LS/BR

07 March 2019

**Report 337184**

**Page 2 of 3**

**Flammability in accordance with IMO 2010 FTP CODE ANNEX 1 PART 8**

**Conditioning**

A minimum of 24 hours at 65±5% Relative Humidity, 20±5°C

**Report**

**Flame application time:** 15 seconds

**Mode of flame application:** Edge ignition

The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a configuration.

Face	Warp direction					Weft direction				
	1	2	3	4	5	1	2	3	4	5
<b>Specimen number</b>										
<b>Flame reached and edge (✓ or X)</b>	X	X	X	X	X	X	X	X	X	X
<b>Hole reach an edge (✓ or X)</b>	X	X	X	X	X	X	X	X	X	X
<b>Surface flash (✓ or X)</b>	X	X	X	X	X	X	X	X	X	X
<b>Duration of flaming (s)</b>	0	0	0	0	0	0	0	0	0	0
<b>Length of char (mm)</b>	53	62	39	38	75	63	97	109	74	66
<b>Ignition of Cotton wool (Y/N)</b>	N	N	N	N	N	N	N	N	N	N

**Mean Char Length Warp= 45mm Weft= 84mm**

Our Ref: SW/LS/BR

07 March 2019

**Report 337184**

**Page 3 of 3**

**Flame application time:** 15 seconds

**Mode of flame application:** Edge ignition

The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a configuration.

Face	Warp direction					Weft direction				
	1	2	3	4	5	1	2	3	4	5
<b>Specimen number</b>										
<b>Flame reached and edge (✓ or X)</b>	X	X	X	X	X	X	X	X	X	X
<b>Hole reach an edge (✓ or X)</b>	X	X	X	X	X	X	X	X	X	X
<b>Surface flash (✓ or X)</b>	X	X	X	X	X	X	X	X	X	X
<b>Duration of flaming (s)</b>	0	0	0	0	0	0	0	0	0	0
<b>Length of char (mm)</b>	9	51	59	66	54	52	55	53	59	58
<b>Ignition of Cotton wool (Y/N)</b>	N	N	N	N	N	N	N	N	N	N

**Mean Char Length Warp= 58mm Weft= 55mm**

**Comments**

On the basis of the tests carried out this sample of fabric meets the performance criteria for curtains and drapes as specified in Clause 3 of IMO 2010 FTP CODE ANNEX 1 PART 7.