



**Indetex nv**  
**Rue du Mont Gallois 58**  
**7700 MOUSCRON**

**Your notice of**  
12-05-2023

**Your reference**

**Date**  
22-05-2023

## Analysis Report 23.02730.03

Required tests :

**EN 13773 (2003)**

Sample id	Information given by the client	Date of receipt
T2311633	BOREALE - IMOLA	12-05-2023

Gina Créelle  
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2311633\_01d - BOREALE - IMOLA

**Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.**

Date of ending the test	22-05-2023
Standard used	EN 1101 (1995) + A1 (2005)
Product standard	EN 13773 (2003)
Deviation from the standard	-
Conditioning	20°C, relative humidity 65%
Testing atmosphere	23°C, relative humidity 53%
Ignition	Bottom edge

The test specimens have been washed 3 times instead of 12 times.

### Length

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	3
4	2	1
5	0	1
6	0	2
7	1	1
8	0	1
9	0	1
10	0	1
11	0	1
12	0	1
13	0	1
14	0	1
15	0	1
16	0	1
17	0	1
18	0	1
19	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated  
 The test requires at least five instances of ignition and five instances of non-ignition.  
 Because less than 5 instances of ignition have been measured, and taking into account §12 of ISO 6940, a 'non-ignition' for this test is recorded

### Width

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated  
 No ignition within 20 s

Reference: T2311633\_01d - BOREALE - IMOLA

**Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.**

Date of ending the test 22-05-2023  
Standard used EN 13772 (2011)  
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have been washed 3 times instead of 12 times.

**Length**

	Front	Back	Front	Front
Severance 1 <sup>st</sup> thread	no	no	no	no
Severance 2 <sup>nd</sup> thread	no	no	no	no
Severance 3 <sup>rd</sup> thread	no	no	no	no
Time to sever 3 <sup>rd</sup> thread (s)	/	/	/	/
Destroyed length (mm)	130	130	135	135
Flaming debris	no	no	no	no

**Width**

	Front	Back	Back	Back
Severance 1 <sup>st</sup> thread	no	no	no	no
Severance 2 <sup>nd</sup> thread	no	no	no	no
Severance 3 <sup>rd</sup> thread	no	no	no	no
Time to sever 3 <sup>rd</sup> thread (s)	/	/	/	/
Destroyed length (mm)	125	135	130	130
Flaming debris	no	no	no	no

**Classification in accordance with EN 13773 Class 1**