



Indetex nv
Dhr. Jan De Praeter
Rue du Mont Gallois 58
7700 MOUSCRON

Your notice of
28-08-2020

Your reference

Date
18-09-2020

Analysis Report 20.05198.05

Required tests :

EN 13773 (2003)

Sample id	Information given by the client	Date of receipt
T2018425	MONTECARLO	28-08-2020

Mike De Vrieze
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2018425 - MONTECARLO

Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.

Date of ending the test	01-09-2020
Standard used	EN 1101 (1995) + A1 (2005)
Product standard	EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

Ignition Bottom edge

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.



Length

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	2
4	1	1
5	0	1
6	0	1
7	0	2
8	1	1
9	0	1
10	0	1
11	0	1
12	0	1
13	0	1
14	0	1
15	0	1
16	0	1
17	0	1
18	0	1
19	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated
 The test requires at least five instances of ignition and five instances of non-ignition.
 Because less than 5 instances of ignition have been measured, and taking into account §12 of ISO 6940, a 'non-ignition' for this test is recorded

Width

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated
No ignition within 20 s

Reference: T2018425 - MONTECARLO

Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.

Date of ending the test 02-09-2020
 Standard used EN 13772 (2011)
 Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

	Face A	Face B	Face B	Face B
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	130	135	140	135
Flaming debris	no	no	no	no

Width

	Face A	Face B	Face A	Face A
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	140	135	130	130
Flaming debris	no	no	no	no

Classification in accordance with EN 13773 Class 1